



Technical Data Sheet / *eurocrete* TF

Description

eurocrete TF is a solvent-free high-build coating based upon polyurethane technology which provides excellent resistances to abrasion, chemical attack and other physical aggression.

Composition

A polyurethane resin system combined with abrasion resistant fine fillers.

Appearance

Provides a smooth semi gloss surface finish in a range of colours. Also available in clear.

Durability

Excellent long-term wear resistance can be expected from a two-coat application.

Thickness

Nominal 15-20 mils, dependent upon application rate and number of coats.

Typical Installations

Used in areas requiring good wear and chemical resistance combined with economical cost. It is suitable for chemical storage areas, warehousing, toilets, laboratories, food preparation areas.

Substrates

Adheres well to concrete, grano, metals and asphalts.

Cleaning and Maintenance

Readily cleaned using a propriety cleaning solution.

Cure Schedule

	<u>Coloured</u>	<u>Clear</u>
Pot Life at 20° C	15 minutes	30 minutes
Initial film cure at 20° C	60 minutes	8 hours
Overcoat period at 20° C	16 hours	16 hours
Light traffic at 20° C	24 hours	24 hours
Full cure at 20° C	5 days	5-7 days

Chemical Resistance

Good resistance to a wide range of chemicals.

Colours Available

Available in *eurocrete* standard colours – Red, Grey, Blue and Buff. Custom colours are available; see RAL# standard colours.

Health and Safety

See MSDS sheets.

eurocrete - Division of Bedford Industries Ltd.

Unit #1 – 9452 193 A Street
Surrey, BC V4N 4N4 Canada
Phone: 604-513-5855
Fax: 604-882-9571
Website: www.eurocrete.com